

CONSTRUCTION STRUCTURE STRUKTUR STRUCTUR	Tufting 1/10" sawto Tufté 1/10" sawto Gesäufte 1/10" sawto Gesäufte 1/10" sawto	PERMANENTLY ANTISTATIC ANTISTATIC PERMANENT PERMANENT ANTISTATISCH PERMANENT ANTISTATISCH	ISO 4916 s 2 NF
PILE MATERIAL COMPOSITION DU VELOURS POLYMATERIAU POOLMATERIAAL	100% PVA 3 MPBS*	IMPACT NOISE RATING ISOLATION PHONIQUE TRITTSCHALLVERBESSERUNG GELUDDISOLATE	ISO 140-8 26 dB(A)w
PRIMARY BACKING SUPPORT TRÄGERMATERIAU TUFTDOEK	Non woven PES Non tissé Vlies Vlies	SOUND ABSORPTION ABSORPTION PHONIQUE SCHALLABSORPTIONSGRAD GELUDDABSORPTIE	ISO 954 8,29 Gw
SECONDARY BACKING DOSSIER ROCKEN TAPJUTRAAG	Acrylic Back	THERMAL RESISTANCE RÉSISTANCE THERMIQUE WÄRMEDURCHLASSWIDERSTAND WARMEDOORLAAIWERSTAND	ISO 8982 8,08 W/m² K/W
PILE WEIGHT POIDS DU VELOURS POLDASATOGEWICHT POOLGEWICHT	Ca. 1.150 g/m²	FASTNESS TO LIGHT SOLIDITÉ À LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	ISO 105-B02 s 5-6
TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	Ca. 2.090 g/m²	COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHEIT WATERECHEID	EN ISO 105-E05 s 4-5
PILE HEIGHT ÉPAISSEUR DU VELOURS POLHÖHE POOLHOOGTE	Ca. 5 mm	FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13637-1 Bfl-s1 of gfl-s1
TOTAL HEIGHT ÉPAISSEUR TOTAL GESAMTHÖHE TOTAAL Dikte	Ca. 7 mm	RUBBING FASTNESS SOLIDITÉ AU FROUETEMENT REIBECHEIT WRIJECHEID	EN ISO 105-A12 s 1
FLUFT DENSITY NOMBRE DE POINTS NOPPENZAHL AANTAL, PUNTEN	Ca. 300 000/m²	WIDTH LARGEUR BREITE BREIDTE	EN ISO 9018 ca. 400 cm
PILE DENSITY DENSITÉ DU VELOURS POLDICHTE POOLDICHTHEID	Ca. 8/157 g/cm³		
CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1897 B5 - UC4		
UPEC UPEPES 03 Certification CSTB 16273			
CASTOR CHAIR SUITABILITY CHAISE À ROULETTES STUHLROLLENGEUNG ROLSTOELGEGSCHICTHEID	EN 1385 A: intensive use		
STAIR SUITABILITY ESCALIERS TREPPENGANGUNG TRAPPENGESCHICTHEID	EN 1382 A: intermittent use		



UPEC
CSTB



REG. N°
FRCC858

