



	PRODUCT CHARACTERISTICS			
	Standard	Requirement	Unit	Results
PRODUCT DESCRIPTION				
Traitement de Surface	-	-	-	ProtecSol®
Complexe de Surface	-	-	-	D-Max+
Mousse	-	-	-	CXP HD
Epaisseur	EN 428	-	mm	6.2 mm
Poids	EN 430	-	kg/m ²	4,2
Longueur	EN 426	-	lm	20.5 Standard
Largeur	EN 426	-	lm	1,5
Impact Comfort Index	AC- P90-205	-	%	ICI = 52%
SPORT PROPERTIES				
Shock absorption	EN 14808	≥ 25	%	P1
Vertical deformation	EN 14809	≤ 3.5	mm	≤ 2
Energy return	NF P 90 203	≥ 0.31	m/s	≥ 0.31
Sliding coefficient	EN 13036-4	80 à 110	-	80 - 110
Ball bounce	EN 12235	≥ 90	%	≥ 90
Ball speed	UEFA	50 à 65	cm	-
	ITF	-	-	-
TECHNICAL CHARACTERISTICS				
Abrasion resistance	EN ISO 5470-1	≤ 1000	mg	≤ 350
Impact resistance	EN 1517	≥ 8	N/m	≥ 8
Indentation resistance	EN 1516	≤ 0.5	mm	≤ 0.25
CLASSIFICATION				
Fire	EN 13501-1	-	-	C _{fl} -s1
Anti-bacterial activity (E. coli - S. aureus - MRSA) (3)	ISO 22196	-	-	> 99 % inhibits growth
DECLARATION OF PERFORMANCE				
CE	DOP n°xxx	-	-	Fire Shock Absorption Sliding Coefficient Abrasion Resistance Resistance to rolling load

	METHODE D'INSTALLATION		
	Recommandation GERFLOR	Unité	Résultat
Glued installation: "Original"	Level of dampness of the subfloor	%	RH < 80% (BS 8203) or < 4.5% humidity (CCM)
Installation on Isolsport: "Flexible"		%	RH < 80% (BS 8203) or < 7.0% humidity (CCM)

COLOUR RANGE	
	6109 Framboise

(3) The implementation of an effective cleaning method is the best defence against infection



Health & Safety Life Cycle Analysis



ISO 14001



Recycling

