



	PRODUCT CHARACTERISTICS			
	Standard	Requirement	Unit	Results
PRODUCT DESCRIPTION				
Surface treatment	-	-	-	ProtecSol®
Surface complex	-	-	-	D-Max®
Foam	-	-	-	CXP HD
Thickness	EN 428	-	mm	7 mm
Weight	EN 430	-	kg/m ²	4,6
Length	EN 426	-	lm	26.4 max
Width	EN 426	-	lm	1,5
Impact Protection Index	AC- P90-205	-	%	IPI = 73%
SPORT PROPERTIES				
Shock absorption	EN 14808	≥ 25	%	P1
Vertical deformation	EN 14809	≤ 3.5	mm	≤ 2
Energy return	NF P 90 203	≥ 0.31	m/s	≥ 0.31
Sliding coefficient	EN 13036-4	80 to 110	-	80 - 110
Ball bounce	EN 12235	≥ 90	%	≥ 90
Ball speed	UEFA	50 to 65	cm	-
	ITF	-	-	-
TECHNICAL CHARACTERISTICS				
Abrasion resistance	EN ISO 5470-1	≤ 1000	mg	≤ 350
Impact resistance	EN 1517	≥ 8	N/m	≥ 8
Indentation resistance	EN 1516	≤ 0.5	mm	≤ 0.5
CLASSIFICATION				
Fire	EN 13501-1	-	-	Cfl-s1
Anti-bacterial activity (E. coli - S. aureus - MRSA) (3)	ISO 22196	-	-	> 99 % inhibits growth
DECLARATION OF PERFORMANCE				
	DOP n°xxx	-	-	Fire Shock Absorption Sliding Coefficient Abrasion Resistance Resistance to rolling load

	INSTALLATION METHODS		
	Gerflor's recommendation	Unit	Results
Glued installation: "Original"	Level of dampness of the subfloor	%	RH < 80% (BS 8203) or < 4.5% humidity (CCM)
Installation on Isolport: "Flexible"		%	RH < 80% (BS 8203) or < 7.0% humidity (CCM)
Dry-Text™ System		%	No limit (no dripping water on the slab)

COLOUR RANGE	
6381 Maple Design 6375 Oak Design 6211 Gold 6038 Terracotta 6159 Pink 6146 Coral 6180 Red 6559 Spring 6557 Forest 6570 Mint Green 2404 London Light Blue 6445 Lagoon 6430 Blue 6431 Teal 6758 Silver Gray 6873 Anthracite 3764 Taupe 6347 Beige 6830 Black Standard roll 20.5 ml	TARAFLEX™ SPORT M EVOLUTION

(3) The implementation of an effective cleaning method is the best defence against infection

