

TECHNICAL INFORMATION

Physical properties

Total weight: 400g/m²

Vinyl Weight: 360g/m²

Substrate Type: 100% Woven Cotton – Cotton Scrim

Substrate weight: 40g/m²

Type II and other specifications available

Tensile Strength: MD 40 N/cm (nominal)

TD 30 N/cm (nominal)

Tear Strength: 4500 mN (nominal)

Roll size:

130cm x 30m - cut lengths available

Pattern Repeat

Vertical: Free match

Horizontal: 1300mm

Fire Rating:

Class 'O' to the requirements of Approved

Document B of the British Building

Regulations (Class 1, BS 476 part 7).

Euroclass B - s2, d0. Class A ASTM E-84

Tunnel Test.

Adhesive:

Fabric backed vinyls - Newmor Heavy.

Varies with substrate - please enquire.

Bacteria Resistance:

Manufactured to include antimicrobial

protection as standard to help

in the control of fungi, actinomycetes

and bacteria.

Light Fast:

Excellent Light Fastness

BS EN ISO 105-B02 min. 7/8

LRV = Light reflective value

Specifications

Conforms to requirements of BS EN 15102,

BS EN 259 and Federal Specification

CCC-W-408A & C CFFA Quality Standard

for Vinyl Coated Fabric Wallcoverings

CFFA-W-101A

Stain/Chemical Resistance:

Pass ASTM D-1308-1987 Federal Spot Test.

Resistant to temporary staining of oils,

fats, mild acids and alkalis.

Quality Assurance:

All management systems and production

procedures comply with ISO 9001, the

internationally recognised Quality

Standard.

Availability:

Every product stocked in depth.

5.00pm deadline for next day delivery.

(UK only)

Origin:

Designed, coloured, manufactured and

stocked in the UK.

Warranty:

Newmor offers a five year warranty

against manufacturing defects.

Full details available on application.

Samples:

Larger samples are readily available on

request.

Maintenance:

Fully washable and in most cases products

can be scrubbed repeatedly to remove any

marks without damaging the product itself.

Most products are also able to withstand

the use of chlorine cleaning agents.



www.newmor.com

PREMIER COLLECTION



Newmor
WALLCOVERINGS

UK SALES:

T: 0870 606 1237

E: sales@newmor.com

EXPORT SALES:

T: + 44 (0) 1938 55 2671

E: enquires@newmor.com