

TECHNICAL INFORMATION



Physical properties

Total weight: 460g/m² (nominal)

Vinyl Weight: 400g/m² (nominal)



Substrate Type: Osnaburg Scrim

Fabric Backer

Substrate weight: 60g/m² (nominal)

Other specifications available

Tensile Strength: MD 80 N/cm (nominal)

TD 60 N/cm (nominal)

Tear Strength: 8500 mN (nominal)



Roll size:

130cm x 30m - cut lengths available



Fire Rating:

Class 'O' to the requirements of Approved Document B of the British Building Regulations. Euroclass B - s1, d0.

Class A ASTM E-84 Tunnel Test.



Adhesive:

Fabric backed vinyls - Newmor Heavy.

Varies with substrate - please enquire.



Bacteria Resistance:

Contains an active Fungicide.



Light Fast:

Excellent Light Fastness

BS EN ISO 105-B02 min. 6

Light reflective value (LRV)

In architecture, light reflective value, is a measure of visible and usable light that is reflected from a surface when illuminated by light source.

REB 001 77

REB 002 58

REB 003 26

REB 004 26

REB 005 14

REB 006 13

REB 007 55

REB 008 44

REB 009 32

REB 010 21

REB 011 9

REB 012 4

Specifications

Conforms to requirements of BS EN 15102, BS EN 259 and WA - Quality Standard W-101.

Stain/Chemical Resistance:

Resistant to temporary staining of oils, fats, mild acids and alkalis.

Quality Assurance:

Our management systems and production procedures comply with ISO 9001 : 2015, the Internationally recognised Quality Standard.

Availability:

Every product stocked in depth.
5.00pm deadline for next day delivery.
(UK only)

Origin:

Designed, coloured, manufactured and stocked in the UK.

Warranty:

Newmor offers a five year warranty against manufacturing defects.
Full details available on application.

Samples:

Larger samples are readily available on request.

Maintenance:

Fully washable and in most cases products can be scrubbed repeatedly to remove any marks without damaging the product itself. Also able to withstand the use of chlorine releasing agent solutions.



FM 23833



British Product | Global Support



Newmor
WALLCOVERINGS

UK SALES:

T: 01938 551990

E: sales@newmor.com

EXPORT SALES:

T: + 44 (0) 1938 55 2671

E: enquires@newmor.com